



Conwed Fibers[®] EnviroBlend[®] with TriFlo[™] Hydraulic Mulch — Wood/Cellulose Blend



Description

Conwed Fibers[®] EnviroBlend[®] with TriFlo[™] is a fully biodegradable, Hydraulic Mulch (HM) composed of 100% recycled Thermally Refined[™] wood fibers and 100% recycled paper. The HM is phyto-sanitized, free from plastic netting, and upon application forms an intimate bond with the soil surface to create a porous and absorbent layer that enhances germination and plant growth.

Recommended Applications

- Erosion control and revegetation for mild slopes (≤3H:1V)
- Rough graded slopes
- Enhancement of vegetation establishment

Technical Data

Physical Properties*	Test Method	Units	Minimum Value
Water Holding Capacity	ASTM D7367	%	1000
Material Color	Observed	n/a	Green
Performance Properties*	Test Method	Units	Value
Cover Factor ¹	Large Scale ²	n/a	0.65 maximum
Percent Effectiveness ³	Large Scale ²	%	35 minimum
Environmental Properties*	Test Method	Units	Typical Value
Functional Longevity ⁴	ASTM D5338	n/a	Up to 3 months
Ecotoxicity	EPA 2021.0	%	96-hr LC50 > 100%
Biodegradability	ASTM D5338	%	100
Product Composition			Typical Value
Thermally Processed Wood Fiber ⁵ (minimum)			70%
Cellulose Fiber (maximum)			30%
TriFlo			< 1%

* When uniformly applied at a rate of 2000 pounds per acre (2250 kilograms/hectare) under laboratory conditions. 1. Cover Factor is calculated as soil loss ratio of treated surface versus an untreated control surface. 2. Large scale testing conducted at Utah Water Research Laboratory. For specific testing information please contact a Profile technical service representative at 866-325-6262. 3. % Effectiveness = One minus Cover Factor multiplied by 100%. 4. Functional Longevity is the estimated time period, based upon ASTM D5338 testing and field observations, that a material can be anticipated to provide erosion control and agronomic benefits as influenced by composition, as well as site-specific conditions, including; but not limited to – temperature, moisture, light conditions, soils, biological activity, vegetative establishment and other environmental factors. 5. Heated within a pressurized vessel to a temperature greater than 380 degrees Fahrenheit (193 degrees Celsius) for 5 minutes at a pressure greater than 50 psi (345 kPa) in order to be Thermally Refined[™]/Processed and to achieve phyto-sanitization.

Packaging Data

Properties	Test Method	Units	Nominal Value
Bag Weight	Scale	kg (lb)	22.7 (50)
Bags per Pallet	Observed	#	40

UV and weather-resistant plastic bags. Pallets are weather-proof stretch wrapped with UV resistant pallet cover.

Offered by: Sitework, Erosion & Seeding Supply Company
209 Cane Creek Rd, Fletcher NC 28732
828-654-8990 - www.sesscompany.com

To the best of our knowledge, the information contained herein is accurate. However, Profile Products cannot assume any liability whatsoever for the accuracy or completeness thereof. Final determination of the suitability of any information or material for the use contemplated, of its manner of use and whether the suggested use infringes any patents is the sole responsibility of the user.